

# Foampack® PL

Medium and low density non crosslinked closed cell PE foam laminated planks.

- Great shock absorption over a wide range of drop heights and multiple impacts.
- CFCs & HCFCs free
- 100% Recyclable.

Properties	Standard	PL200	PL300	PL500
Density (kg/m <sup>3</sup> )	ISO 845	25±3	30±5	50±5
Compression resistance (Kpa):	ISO 844			
-10%		15	18	27
-25%		32	36	48
-50%		87	91	108
Compression set, 25%, 22h (%)	ISO 856			
• After 30 min		14	12	8
• After 24h		9	7	4
Water absorption (kg/m <sup>2</sup> )	EN1609	<0,02	<0,02	<0,02
Maximum working temperature (°C)	Internal	80	80	90

Colour: white (others available under request)

Length: 120-275cm

Width: 120cm

