

Foampack® PL

Medium and low density non crosslinked closed cell PE foam laminated planks.

- Great shock absorption over a wide range of drop heights and multiple impacts.
- CFCs & HCFCs free
- 100% Recyclable.

Properties	Standard	PL300	PL500
Density (kg/m ³)	ISO 845	25±5	50±5
Compression resistance (Kpa):	ISO 844		
-10%		18	27
-25%		36	48
-50%		91	108
Compression set, 25%, 22h (%)	ISO 856		
• After 30 min		12	8
• After 24h		7	4
Water absorption (kg/m ²)	EN1609	<0,02	<0,02
Maximum working temperature (°C)	Internal	80	90

Colour: white (others available under request)

Length: 120-275cm

Width: 120cm



Contains min. 30% recycled material

P.I. La Serra II. 25320 Anglesola—Lleida

Tlf: +34-973308518.

www.okcompany.com / infotec@okcompany.com



OVERSEAS KONSTELLATION
COMPANY S.A.

JANUARY 2023